

602063600
COATED FSC®-R400-YG_J

Face	One side coated paper, FSC Mix Credit, is designed for high-end, pressure sensitive label applications. This grade features excellent opacity and high brightness combined with a semi-gloss finish for excellent printability.
Adhesive	Acrylic based, removable adhesive for general use with long term removability.
Liner	Yellow, FSC Mix Credit, supercalendered siliconised glassine paper. Specially designed for high-speed conversion, punching and perforation. Transparency allows its use in automatic dispensing system.

Face	Method	Unit	Target	
Basis Weight	ISO 536	g/m ²	78 ± 4	
Thickness	ISO 534	µm	67 ± 4	
Adhesive				
Peel adhesion 90°	FTM 2 st.st	N/m	min.40	(min. 1 N/25mm)
Loop Tack	FTM 9 glass	N/m	min.150	(min. 3,75 N/25mm)
Min. appl. temperature		°C	0	
Service temperature		°C	-20 /	
Liner				
Basis Weight	ISO 536	g/m ²	56 ± 2	
Thickness	ISO 534	µm	50 ± 3	
Transparency	DIN 53147	%	49	
Laminate				
Thickness	ISO 534	µm	130 ± 5	

Application and use

The product is suitable for removable labels for stores and supermarkets, process labelling applications and industrial labelling.

Conversion and Printing

Surface is suitable for excellent printing quality by all conventional print technologies and thermal transfer printing.

Packaging

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

Shelf Life and Storage Conditions

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 ° C ± 2 ° C with a relative humidity of 50 %, ± 5%.

Sustainability

The product is sold as FSC® Mix Credit under Frimpeks Ltd
 FSC® Certificate INT-COC-002144
 FSC® License FSC-C160714



All information and recommendations about Frimpeks products are based on our existing knowledge and experiences but do not mean a guarantee or warranty. As the products are used for different applications we recommend checking suitability of product prior to use. All information is subject to change without notice. End user obliged and verifies the above information before using the material.