



651801010

VACUUM METALLISED SILVER TC3 -P100- YG_D 651801010

Face	A bright silver, vacuum	n metallised woodfree printing	g paper with a glossy pri	nt receptive lacquer.
------	-------------------------	--------------------------------	---------------------------	-----------------------

Adhesive Acrylic based, permanent adhesive for general use. Suitable for numerous applications on clean, dry

and flat surfaces, including slightly rough and curved substrates. It's not suitable for wet applications.

Excellent performance during slitting, high speed matrix-stripping and automatic labelling.

Liner Yellow, supercalandered siliconised glassine paper. Specially designed for high speed conversion,

punching and perforation. Transparency allows its use in automatic dispensing system.

Face	Method	Unit	Target	
Basis Weight	ISO 536	g/m²	80 ± 3	
Thickness	ISO 534	μm	67 ± 3	
Adhesive				
Peel adhesion 90°	FTM 2 st.st	N/m	min.240	(min. 6 N/25mm)
Loop Tack	FTM 9 glass	N/m	min.480	(min. 12 N/25mm)
Min. appl temperature		°C	0	
Service temperature		°C	-20 / +80	
Liner				
Basis Weight	ISO 536	g/m²	60 ± 2	
Thickness	ISO 534	μm	51 ± 3	
Transparency	DIN 53147	%	49	
Laminate				
Thickness	ISO 534	μm	125 ± 5	

Application and use

This product suitable for primary labelling of high and luxury goods like wines, spirits, beverages, foods, stickers and promotional labelling.

Conversion and Printing

Suitable to flexo, letterpress, gravure and screen printing. Overvarnishing is recommended to improve durability of print and surface. Exposing to high temperature might have negative influence on face material's gloss.

Packaging

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

Shelf Life and Storage Conditions

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 $^{\circ}$ C \pm 2 $^{\circ}$ C with a relative humidity of 50 %, \pm 5%.

All information and recommendations about Frimpeks products are based on our existing knowledge and experiences but do not mean a guarantee or warranty. As the products are used for different applications we recommend checking suitability of product prior to use. All information is subject to change without notice. End user obliged and verifies the above information before using the material.