

**652064690**
**COATED BOARD 130G FSC-DF710-YG\_D**

<b>Face</b>	A glossy, 2-side coated woodfree board for high quality label where high stiffness is required.
<b>Adhesive</b>	Acrylic based, permanent adhesive suitable for deep freeze applications onto cold and moist surfaces with very good adhesion at low temperature. Not suitable for curved surface labelling.
<b>Liner</b>	Yellow, supercalendered siliconised glassine paper. Specially designed for high-speed conversion, punching and perforation. Transparency allows its use in automatic dispensing system.

<b>Face</b>	<b>Method</b>	<b>Unit</b>	<b>Target</b>	
Basis Weight	ISO 536	g/m <sup>2</sup>	130 ± 5	
Thickness	ISO 534	µm	98 ± 4	
<b>Adhesive</b>				
Peel adhesion 90°	FTM 2 st.st	N/m	min.220	(min. 5,5 N/25mm)
Loop Tack	FTM 9 glass	N/m	min.400	(min. 10 N/25mm)
Min. appl. temperature		°C	-20	
Service temperature		°C	-40 / +70	
<b>Liner</b>				
Basis Weight	ISO 536	g/m <sup>2</sup>	56 ± 2	
Thickness	ISO 534	µm	50 ± 3	
Transparency	DIN 53147	%	49	
<b>Laminate</b>				
Thickness	ISO 534	µm	168 ± 5	

### Application and use

This product is designed for low temperature and deep freeze conditions where a stiff, high quality label is required.

### Conversion and Printing

Surface is suitable for excellent printing quality by all conventional print technologies and thermal transfer printing.

### Packaging

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

### Shelf Life and Storage Conditions

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 °C ± 2 °C with a relative humidity of 50 %, ± 5%.

### Sustainability

The product is sold as FSC® Mix Credit under Frimpeks Ltd

FSC® Certificate INT-COC-002144

FSC® License FSC-C160714.



All information and recommendations about Frimpeks products are based on our existing knowledge and experiences but do not mean a guarantee or warranty. As the products are used for different applications we recommend checking suitability of product prior to use. All information is subject to change without notice. End user obliged and verifies the above information before using the material.