



652403600

VELLUM EXTRA-H400-YG D

Face	A white, surface-sized, calendered woodfree printing paper with smooth surface.
------	---

Adhesive Rubber based hotmelt, permanent adhesive for general use. Excellent adhesive performence on a wide

variety of substrates including apolar, slightly rough and curved substrates. Particularly good perfomance at lower temperatures, we recommend to check suitability prior to use. Excellent

performance during slitting, high speed matrix-stripping and automatic labelling.

Liner Yellow, supercalandered siliconised glassine paper. Specially designed for high speed conversion,

punching and perforation. Transparency allows its use in automatic dispensing system.

Face	Method	Unit	Target	
Basis Weight	ISO 536	g/m²	68 ± 3	
Thickness	ISO 534	μm	67 ± 3	
Adhesive				
Peel adhesion 90°	FTM 2 st.st	N/m	min.240	(min. 6 N/25mm)
Loop Tack	FTM 9 glass	N/m	Min.480	(min. 12 N/25mm)
Min. appl temperature		°C	0	
Service temperature		°C	-30 / +70	
Liner				
Basis Weight	ISO 536	g/m²	56 ± 2	
Thickness	ISO 534	μm	50 ± 3	
Transparency	DIN 53147	%	49	
Laminate				
Thickness	ISO 534	μm	125 ± 5	

Application and use

For use in logistics labelling, warehouse inventory labelling, other in-house product identification labelling, commercial and general labelling.

Conversion and Printing

Surface is suitable for excellent printing quality by all conventional print technologies and thermal transfer printing.

Packaging

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

Shelf Life and Storage Conditions

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 $^{\circ}$ C \pm 2 $^{\circ}$ C with a relative humidity of 50 %, \pm 5%.

Rev.Date:

All information and recommendations about Frimpeks products are based on our existing knowledge and experiences but do not mean a guarantee or warranty. As the products are used for different applications we recommend checking suitability of product prior to use. All information is subject to change without notice. End user obliged and verifies the above information before using the material.