

652404315

VELLUM EXTRA SAND. -P100/P100- WG/YG D 652404315

Face A white, surface-sized, calendered woodfree printing paper with smooth surface.

Adhesive Acrylic based, permanent adhesive for general use. Suitable for numerous applications on clean, dry

and flat surfaces, including slightly rough and curved substrates. It's not suitable for wet applications.

Excellent performance during slitting, high speed matrix-stripping and automatic labelling.

Liner Supercalandered siliconised glassine paper. Specially designed for high speed conversion, punching

and perforation. Transparency allows its use in automatic dispensing system.

| ce | Method | Unit | Target | |
|---------------------|-------------|------|-----------|------------------|
| sis Weight | ISO 536 | g/m² | 70 ± 3 | |
| ickness | ISO 534 | μm | 67 ± 3 | |
| lhesive | | | | |
| el adhesion 90° | FTM 2 st.st | N/m | min.240 | (min. 6 N/25mm) |
| op Tack | FTM 9 glass | N/m | min.480 | (min. 12 N/25mm) |
| n. appl temperature | | °C | 0 | |
| vice temperature | | °C | -20 / +80 | |
| er | | | | |
| is Weight | ISO 536 | g/m² | 60 ± 2 | |
| kness | ISO 534 | μm | 51 ± 3 | |
| nsparency(white) | DIN 53147 | % | 51 | |
| ansparency(yellow) | DIN 53147 | % | 49 | |
| minate | | | | |
| ckness | ISO 534 | μm | 190 ± 5 | |

Application and use

This sandwich construction consisting of usually two self-adhesive layers on top of each other (additional layers possible on request) Functional label applications where a second (or third) self adhesive label is needed when the first layer has been peeled off or applied e.g. promotional stickers on consumer products.

Conversion and Printing

Surface is suitable for excellent printing quality by all conventional print technologies and thermal transfer printing.

Packaging

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

Shelf Life and Storage Conditions

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 $^{\circ}$ C \pm 2 $^{\circ}$ C with a relative humidity of 50 %, \pm 5%.

Page Number: 1/1

All information and recommendations about Frimpeks products are based on our existing knowledge and experiences but do not mean a guarantee or warranty. As the products are used for different applications we recommend checking suitability of product prior to use. All information is subject to change without notice. End user obliged and verifies the above information before using the material.