

**652442405**
**VELLUM EXTRA FSC®-PE300-YG\_D**

<b>Face</b>	A white, surface-sized, calendared woodfree printing FSC Mix Credit paper with smooth surface
<b>Adhesive</b>	Acrylic based, strong permanent adhesive for general use. This adhesive gives excellent initial tack and adhesion even on a wide variety substrate including apolar, rough and curved substrates.
<b>Liner</b>	Yellow, FSC Mix Credit, supercalendered siliconised glassine paper. Specially designed for high-speed conversion, punching and perforation. Transparency allows its use in automatic dispensing system.

Face	Method	Unit	Target	
Basis Weight	ISO 536	g/m <sup>2</sup>	68 ± 3	
Thickness	ISO 534	µm	67 ± 3	
<b>Adhesive</b>				
Peel adhesion 90°	FTM 2 st.st	N/m	min.275	(min. 6,875 N/25mm)
Loop Tack	FTM 9 glass	N/m	min.550	(min. 13,75 N/25mm)
Min. appl. temperature		°C	+5	
Service temperature		°C	-20 / +80	
<b>Liner</b>				
Basis Weight	ISO 536	g/m <sup>2</sup>	56 ± 2	
Thickness	ISO 534	µm	50 ± 3	
Transparency	DIN 53147	%	49	
<b>Laminate</b>				
Thickness	ISO 534	µm	130 ± 5	

**Application and use**

For use in logistics labelling, warehouse inventory labelling, other in-house product identification labelling, commercial and general labelling.

**Conversion and Printing**

Surface is suitable for excellent printing quality by all conventional print technologies and thermal transfer printing.

**Packaging**

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

**Shelf Life and Storage Conditions**

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 °C ± 2 °C with a relative humidity of 50 %, ± 5%.

**Sustainability**

The product is sold as FSC® Mix Credit under Frimpeks Ltd  
 FSC® Certificate INT-COC-002144  
 FSC® License FSC-C160714

