

**653102005**
**TOP THERMAL -PE300- YG\_D**

<b>Face</b>	A white topcoated paper that is coated with black imaging thermosensitive coating. This paper has very good resistance to moisture, oil, fat, alcohol and plasticizers.
<b>Adhesive</b>	Acrylic based, strong permanent adhesive for general use. This adhesive gives excellent initial tack and adhesion even on a wide variety substrates including apolar, rough and curved substrates. Edge bleeding may occur.
<b>Liner</b>	Yellow, supercalandered siliconised glassine paper. Specially designed for high speed conversion, punching and perforation. Transparency allows its use in automatic dispensing system.

<b>Face</b>	<b>Method</b>	<b>Unit</b>	<b>Target</b>	
Basis Weight	ISO 536	g/m <sup>2</sup>	75 ± 5	
Thickness	ISO 534	µm	75 ± 5	
<b>Adhesive</b>				
Peel adhesion 90°	FTM 2 st.st	N/m	min.275	(min. 6,875 N/25mm)
Loop Tack	FTM 9 glass	N/m	min.550	(min. 13,75 N/25mm)
Min. appl temperature		°C	+5	
Service temperature		°C	-20 / +80	
<b>Liner</b>				
Basis Weight	ISO 536	g/m <sup>2</sup>	56 ± 2	
Thickness	ISO 534	µm	50 ± 3	
Transparency	DIN 53147	%	49	
<b>Laminate</b>				
Thickness	ISO 534	µm	137 ± 5	

**Application and use**

Typical applications identification barcode labels for pre-packed food, industrial barcoding for logistics, transport and tracking as well as thermal labels where a good level of image resistance is required.

**Packaging**

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

**Conversion and Printing**

This product has good printability in all classical printing methods. Printing inks should be checked for suitability prior to use. This product is designed for use in thermal printing system at printing speeds up to 8 inch /200 mm per sec (based on printer's set up).

**Shelf Life and Storage Conditions**

One year when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 °C ± 2 °C with a relative humidity of 50 %, ± 5%.