

**654103414**
**PP WHITE 60 TC -H200- PET CLR 23\_D**

<b>Face</b>	A white pearlescent, topcoated polypropylene film with high brilliance and internal reflectivity.
<b>Adhesive</b>	Rubber based hotmelt, permanent adhesive for general use. Provides excellent conversion and adhesive performance on a wide variety of surfaces including non-polar, slightly rough and curved substrates. Displays particularly good performance at lower temperatures. A suitability check prior to use is recommended. Excellent performance during slitting, high speed matrix-stripping and automatic labelling.
<b>Liner</b>	A clear polyester liner giving optimum smoothness to the adhesive layer. High strength and uniform quality permit very high speed conversion and dispensing.

<b>Face</b>	<b>Method</b>	<b>Unit</b>	<b>Target</b>	
Basis Weight	ISO 536	g/m <sup>2</sup>	42 ± 2	
Thickness	ISO 534	µm	60 ± 3	
<b>Adhesive</b>				
Peel adhesion 90°	FTM 2 st.st	N/m	min.300	(min. 7,5 N/25mm)
Loop Tack	FTM 9 glass	N/m	min.600	(min. 15 N/25mm)
Min. appl temperature		°C	0	
Service temperature		°C	-30 / +70	
<b>Liner</b>				
Basis Weight	ISO 536	g/m <sup>2</sup>	32 ± 1,4	
Thickness	ISO 534	µm	23 ± 1	
<b>Laminate</b>				
Thickness	ISO 534	µm	93 ± 5	

**Application and use**

For use in labelling of quality products such as luxury items, cosmetics, toiletries and household chemicals requiring durability and resistance to chemicals or moisture.

**Conversion and Printing**

Topcoated surface is suitable for printing by the usual printing technologies including letterpress, flexo, gravure and screen printing.

**Packaging**

The rolls are sliced according to customer requirements; double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

**Shelf Life and Storage Conditions**

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 °C ± 2 °C with a relative humidity of 50 %, ± 5%.