

654153810

PP MATT WHITE 81 TC-WS820-PET CLR 23 D

Face A white matt, polypropylene film with high opacity, whiteness and good pr	intability.
--	-------------

Adhesive Acrylic based, permanent, non-bleeding adhesive with improved water resistance, good clarity, UV

resistance and short term removability.

Liner A clear polyester liner giving optimum smoothness to the adhesive layer. High strength and uniform

quality permit very high speed conversion and dispensing.

Face	Method	Unit	Target	
Basis Weight	ISO 536	g/m²	57 ± 3	
Thickness	ISO 534	μm	80 ± 5	
Adhesive				
Peel adhesion 90°	FTM 2 st.st	N/m	min. 200	(min. 5 N/25mm)
Loop Tack	FTM 9 glass	N/m	min. 400	(min. 10 N/25mm)
Min. appl temperature		°C	+5	
Service temperature		°C	-20 / +100	
Liner				
Basis Weight	ISO 536	g/m²	32 ± 1,4	
Thickness	ISO 534	μm	23 ± 1	
Laminate				
Thickness	ISO 534	μm	115 ± 5	

Application and use

For use in labelling of quality products such as luxury items, cosmetics, toiletries and household chemicals requiring durability and resistance to chemicals or moisture.

Conversion and Printing

Topcoated surface is suitable for printing by the usual printing technologies including letterpress, flexo, gravure and screen printing.

Packaging

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

Shelf Life and Storage Conditions

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 $^{\circ}$ C \pm 2 $^{\circ}$ C with a relative humidity of 50 %, \pm 5%.

All information and recommendations about Frimpeks products are based on our existing knowledge and experiences but do not mean a guarantee or warranty. As the products are used for different applications we recommend checking suitability of product prior to use. All information is subject to change without notice. End user obliged and verifies the above information before using the material.

Date of Publication: 01.01.2016