

654202521
PP SOLID WHITE 50 TC -WS820- WG_D

Face	A bi-axially oriented, gloss white, topcoated polypropylene film.
Adhesive	Acrylic based, permanent, non-bleeding adhesive with improved water resistance, good clarity, UV resistance and short term removability.
Liner	White, supercalandered siliconised glassine paper. Specially designed for high speed conversion, punching and perforation. Transparency allows its use in automatic dispensing system.

Face	Method	Unit	Target	
Basis Weight	ISO 536	g/m ²	48 ± 3	
Thickness	ISO 534	µm	50 ± 3	
Adhesive				
Peel adhesion 90°	FTM 2 st.st	N/m	min. 200	(min. 5 N/25mm)
Loop Tack	FTM 9 glass	N/m	min. 400	(min. 10 N/25mm)
Min. appl temperature		°C	+5	
Service temperature		°C	-20 / +100	
Liner				
Basis Weight	ISO 536	g/m ²	58 ± 2	
Thickness	ISO 534	µm	50 ± 3	
Transparency	DIN 53147	%	51	
Laminate				
Thickness	ISO 534	µm	110 ± 5	

Application and use

For use in labelling of quality products such as luxury items, cosmetics, toiletries and household chemicals requiring durability and resistance to chemicals or moisture.

Packaging

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

Conversion and Printing

Topcoated surface is suitable for printing by the usual printing technologies including letterpress, flexo, gravure and screen printing.

Shelf Life and Storage Conditions

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 °C ± 2 °C with a relative humidity of 50 %, ± 5%.