

**654702015**
**PP CLEAR 50 TC2 -R410- WG\_D**
**654702015**

<b>Face</b>	A bi-axially oriented, gloss clear, topcoated polypropylene film.
<b>Adhesive</b>	Acrylic based, removable adhesive for general use with long term removability.
<b>Liner</b>	White, supercalandered siliconised glassine paper. Specially designed for high speed conversion, punching and perforation. Transparency allows its use in automatic dispensing system.

<b>Face</b>	<b>Method</b>	<b>Unit</b>	<b>Target</b>	
Basis Weight	ISO 536	g/m <sup>2</sup>	45 ± 2	
Thickness	ISO 534	µm	50 ± 3	
<b>Adhesive</b>				
Peel adhesion 90°	FTM 2 st.st	N/m	min. 80	(min. 2 N/25mm)
Loop Tack	FTM 9 glass	N/m	min. 180	(min. 4,5 N/25mm)
Min. appl temperature		°C	+5	
Service temperature		°C	-20 / +80	
<b>Liner</b>				
Basis Weight	ISO 536	g/m <sup>2</sup>	60 ± 2	
Thickness	ISO 534	µm	51 ± 3	
Transparency	DIN 53147	%	51	
<b>Laminate</b>				
Thickness	ISO 534	µm	112 ± 5	

#### **Application and use**

For use in labelling of the products where completely clean surface is required after peeling the label.

#### **Packaging**

The rolls are sliced according to customer requirements; double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

#### **Conversion and Printing**

Topcoated surface is suitable for printing by the usual printing technologies including letterpress, flexo, gravure and screen printing.

#### **Shelf Life and Storage Conditions**

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 °C ± 2 °C with a relative humidity of 50 %, ± 5%.