

750000041

MAT PP WHITE 80 -H300- W. KRAFT 120 D

Face	A white matt, medium gloss polypropylene film with high opacity and whiteness. Excellent graphical as

well as thermal transfer printability.

Adhesive Rubber based hotmelt, permanent adhesive for general use. Excellent adhesive performence on a wide

variety of substrates including apolar, slightly rough and curved substrates. Particularly good perfomance at lower temperatures, we recommend to check suitability prior to use. Excellent

performance during slitting, high speed matrix-stripping and automatic labelling.

Liner White, woodfree kraft backing paper for optimal layflat performance. Specially designed for laminate

where thin backing is needed.

Face Basis Weight	Method ISO 536	Unit g/m²	Target 60 ± 3		
Thickness	ISO 534	μm	75 ± 5		
Adhesive					
Peel adhesion 90°	FTM 2 st.st	N/m	min.300	(min. 7,5 N/25mm)	
Loop Tack	FTM 9 glass	N/m	min.600	(min. 15 N/25mm)	
Min. appl temperature		°C	0		
Service temperature		°C	-30 / +70		
Liner					
Basis Weight	ISO 536	g/m²	120 ± 4		
Thickness	ISO 534	μm	117 ± 4		
Laminate					
Thickness	ISO 534	μm	115 ± 5		

Application and use

For use in labelling of quality products such as luxury items, cosmetics, toiletries and household chemicals requiring durability and resistance to chemicals or moisture.

Conversion and Printing

Corona treated surface is suitable for printing by the usual printing technologies including letterpress, flexo, gravure and screen printing. In-line corona treatment, careful selection of the ink and trial ink performance before production are strongly recommended. Most TTR wax-ribbons show very good scratch resistance and durability.

Packaging

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

Shelf Life and Storage Conditions

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 °C \pm 2 °C with a relative humidity of 50 %, \pm 5%.

All information and recommendations about Frimpeks products are based on our existing knowledge and experiences but do not mean a guarantee or warranty. As the products are used for different applications we recommend checking suitability of product prior to use. All information is subject to change without notice. End user obliged and verifies the above information before using the material.