



752000031

DSS-WG SAND -DF710/DF710- VELLUM/VELLUM

Medium White, supercalandered double side siliconised glassine paper. Specially designed for high speed

conversion, punching and perforation. Transparency allows its use in automatic dispensing system.

Adhesive Acrylic based, permanent adhesive suitable for deep freeze applications onto cold and moist surfaces

with very good adhesion at low temperature. Not suitable for curved surface labelling.

Face / Liner A white, surface-sized, calendered woodfree printing paper with smooth surface.

Medium	Method	Unit	Target	
Basis Weight	ISO 536	g/m²	58 ± 2	
Thickness	ISO 534	μm	50 ± 3	
Adhesive				
Peel adhesion 90°	FTM 2 st.st	N/m	min.220	(min. 5,5 N/25mm)
Loop Tack	FTM 9 glass	N/m	min.400	(min. 10 N/25mm)
Min. appl temperature		°C	-20	
Service temperature		°C	-40 / +70	
Face / Liner				
Basis Weight	ISO 536	g/m²	70 ± 3	
Thickness	ISO 534	μm	67 ± 3	
Laminate				
Thickness	ISO 534	μm	190 ± 5	

Application and use

This sandwich construction consisting of usually two self-adhesive layers on top of each other (additional layers possible on request) Functional label applications where a second (or third) self adhesive label is needed when the first layer has been peeled off or applied e.g. promotional stickers on consumer products.

Conversion and Printing

Surface is suitable for excellent printing quality by all conventional print technologies and thermal transfer printing.

Packaging

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

Shelf Life and Storage Conditions

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 $^{\circ}$ C \pm 2 $^{\circ}$ C with a relative humidity of 50 %, \pm 5%.

All information and recommendations about Frimpeks products are based on our existing knowledge and experiences but do not mean a guarantee or warranty. As the products are used for different applications we recommend checking suitability of product prior to use. All information is subject to change without notice. End user obliged and verifies the above information before using the material.

Date of Publication: 01.01.2020